



QUALITY REQUIREMENTS FOR WASTE PAPER

| Waste paper type according to EN 643: 2014 (E) | Parameters (%) | | | | | |
|--|----------------|-----------|-----------|-----------------------|--------|-----------|
| | Humidity | Whiteness | Wood mass | Non-ground impurities | Ash | Adhesives |
| First grade (I) | | | | | | |
| 3.05, 3.07, 3.18-3.19 | max 10 | min 80 | max 10 | max 0.5 | max 25 | max 0.5 |
| Second grade (II) | | | | | | |
| 3.02, 3.04, 3.06, 3.09, 3.10, 3.15-3.17 | max 10 | min 70 | max 10 | max 0.5 | max 25 | max 0.5 |
| Third grade (III) | | | | | | |
| 1.06-11, 2.01-2.09, 2.12, 3.08, 3.11, 3.14 | max 10 | min 48 | max 10 | max 0.5 | max 25 | max 1.0 |
| Fourth grade (cardboard) | | | | | | |
| 1.05, 4.01.02-4.03 | max 10 | - | - | max 0.5 | max 25 | max 1.0 |

Waste paper must not contain:

- non-paper admixtures according to EN 643:2014: metal, plastic, glass, textiles, wood, sand, mortar and synthetic materials, synthetic paper;
- paper and cardboard not suitable for processing: paper and cardboard covered with foil, varnish, textile, foil, paraffin, asphalt, rubber;
- contaminated with chemicals or hazardous substances;
- greasy, metallic, sandpaper, paper and cardboard bags for food, construction and chemicals, cardboard covers all books, back parts of books impregnated with adhesives, labels, cardboard nozzles;
- rotten, moldy, burnt paper;
- intensely dyed paper (black, blue, red, etc., other than white);
- paper egg trays.